



Brian Havens, Woodworker

Minimum Wall Thickness Chart

for rough turned bowls

Bowl Diameter	Minimum Wall Thickness
4"	1/2"
5"	1/2"
6"	5/8"
7"	3/4"
8"	7/8"
9"	1"
10"	1"
11"	1 1/8"
12"	1 1/4"
13"	1 3/8"
14"	1 1/2"
15"	1 1/2"
16"	1 5/8"
17"	1 3/4"
18"	1 7/8"
19"	2"
20"	2"